

# Aqua-Pur

Eco-friendly, water-based varnish to protect hardwood floors.

Aqua-Pur is easy to use and apply and does not alter the natural colour of the wood whilst guaranteeing a high degree of scratch-proof protection for wood floors of any type.



1. Single-component, ready to use
2. Easy to apply
3. Maintains the natural colour of the wood
4. High scratch resistance
5. Compliant with Directive 2004/42/EC

## Rating 5

- ✓ VOC Low Emission
- ✓ Water Based
- ✓ Solvent  $\leq 80$  g/kg
- ✓ Low Ecological Impact
- ✓ Health Care



---

## Areas of application

### → Intended use

High scratch-proof finish for:

- traditional wood floors
- prefinished wood floors
- wood floors to be restored
- bamboo floors

Interior wood floors in residential buildings  
subject to medium traffic

Do not use for external use applications or on wood floors in constant or frequent contact with water.

Not recommended for finishing wood floors subject to intense or extreme foot traffic (public offices, entertainment venues, shopping centres, etc.).

---

## Instructions for use

### → Preparation of substrates

Buff the hardwood floors until the surface is smooth, clean and free from oil, grease, wax, silicon and previous coats of varnish. Apply Aqua-Pur Flex (following the instructions on the technical data sheet) to fill cracks and irregularities and/or to smooth surfaces and to ensure even absorption. Wait  $\approx 1 - 2$  hours then sand with 120 grain abrasive mesh disc. Carefully remove any dust created during sanding and wipe away any residues using an antistatic cloth, then apply Aqua-Pur Basic (following the instructions on the technical data sheet) or alternatively, just directly apply Aqua-Pur.

### → Preparation

The product is ready-to-use. Shake thoroughly before use, insert the undercap filter and pour into the appropriately prepared tray. Remove the undercap filter before shutting the can. Dilute to 5 – 10% using clean water or Aqua-Pur Retard if necessary, and mix again. Set aside for 5 minutes before applying.

### → Application

Apply Aqua-Pur or Aqua-Pur Basic or Aqua-Pur Basic Rapid when recommended; using Roller Plus with a coverage of  $\approx 80 - 100$  ml/m<sup>2</sup>. As soon as the floor can take foot traffic and no more than 3 hours later, apply the second finish coat of Aqua-Pur. After  $\approx 10 - 12$  hours, sand with 220 grain abrasive mesh disc; carefully remove any dust created during sanding, wipe away any residues using an anti-static cloth then apply the third coat of Aqua-Pur.

### → Cleaning

Residual traces of Aqua-Pur can be removed from tools with water before the product hardens.

---

## Special notes

- Allow product to reach room temperature before use.
- Use clean containers and tools.
- Once opened, the can must be used as quickly as possible.
- for an even finish, apply evenly in accordance with the recommended quantities.

- Maintenance of hardwood floors: varnished wood floors require regular maintenance. Use Supersoap neutral detergent to clean the surface. Use Refresher or Care Pro for routine or extraordinary maintenance depending on wear.

# Certificates and marks



## Technical Data compliant with Kerakoll Quality Standard

Appearance	translucent yellow-ivory liquid
Pack	5 l cans
Shelf life	≈ 12 months from production in the original sealed packaging
Warning	protect from frost, avoid direct exposure to sunlight and sources of heat
Temperature range for application	from +5° to +30 °C
Sheen	satin ≈ 35 gloss
	matt ≈ 20 gloss
Dust free	≈ 30 min.
Waiting time:	
- for overlaying	≈ 10 – 12 hrs
- for light foot traffic	≈ 36 hrs
- for normal foot traffic	≈ 7 – 10 days
Coverage	≈ 80 – 100 ml/m <sup>2</sup> per coats

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e. temperature, ventilation and absorbency level of the substrate.

## Performance

### VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions

Conformity	EC 1 GEV-Emicode	GEV Cert. 6345/11.01.02
------------	------------------	-------------------------

---

# Warning

- Product for professional use
- abide by any standards and national regulations
- check compatibility (colour, the content of resins, oils and other substances) with less common woods
- remove all residues of previous treatments to ensure an even finish
- always check room/ambient temperature and moisture content of wood
- protect from direct sunlight and air currents for the first 3 hours
- do not use different batches of the product in the same or adjacent environments
- if necessary, ask for the safety data sheet
- for any other issues, contact the Kerakoll Worldwide Global Service 01772 456 831 - [info@kerakoll.co.uk](mailto:info@kerakoll.co.uk)



The Rating classifications refer to the GreenBuilding Rating Manual 2012. This information was last updated in December 2022 (ref. GBR Data Report – 12.22); please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see [www.kerakoll.com](http://www.kerakoll.com). KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building yards and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.