

Water-block Repair

Liquid waterproofing membrane. Liquid hybrid-based waterproofing membrane for roof waterproofing solutions in refurbishment projects.

In 1 kg tin, applicable with a brush or a roller for fast and urgent repairs.



Rating 3

1. Ready-to-use
2. Can also be applied while raining
3. Cold applied, requires no heat or flame
4. Multimaterial
5. Immediate water-resistance
6. Non corrosive
7. High level of durability
8. Without silicone, solvents, bitumen, isocyanates free
9. Excellent adhesion even on damp laying surfaces
10. Excellent resistance to UV rays
11. Overpaintable

- × Regional Mineral $\geq 30\%$
- ✓ VOC Very Low Emission
- ✓ Solvent ≤ 5 g/kg
- × Low Ecological Impact
- ✓ Health Care

kerakoll

areas of use

→ Use

Waterproofing and urgent refurbishments:
gutters, flat roofs, metal or fibre-cement roofs.
Sealing of cracks.
Waterproofing of horizontal and vertical
surfaces: balconies, terraces, foundations...
Waterproofing connection between special roof

parts: vent chimneys, antennas, skylights, side
bands, valley gutters...
Treatment of mechanical anchoring heads (bolts
and nuts).

Instructions for use

→ Substrate preparation

The laying surface must be clean, stable and
free from dust. Remove non-anchored and poorly
cohesive parts.
Water-Block is ready to use and must not be
diluted or mixed with other products.


→ Application

Apply Water-Block Repair with a spreader
or a brush in a ratio of 1.5 to 3 kg / m². Press
firmly against the substrate to guarantee the
best possible sealing and to cross the applied
coats. If necessary, repeat the application after
polymerisation.

Not suitable for polyethylene, polypropylene,
polycarbonate, polymethylmethacrylate,
polytetrafluoroethylene, neoprene and
bituminous bases.

Water-Block does not constitute waterproofing
according to the European Technical Assessment
ETAG 005.

The membrane must not be covered with ceramic
tiles. It is not possible to walk directly on the
membrane, a coating must be put in place.
Do not use under immersion. Do not expose to



WATER-BLOCK
Repair

counterpressure.

After polymerisation, do not subject the
membrane to mechanical anchoring.
The user is responsible for ensuring that the
substrate is compatible in terms of adhesion,
chemical contact and stain formation.
Can be painted after complete drying. Use an
acrylic-based paint and perform a preliminary
compatibility test. Do not use glycerophthalic
paints.

Certificates and marks



* Émission dans l'air intérieur Information sur le niveau d'émission
de substances volatiles dans l'air intérieur, présentant un risque de
toxicité par inhalation, sur une échelle de classe allant de A+ (très
faibles émissions) à C (fortes émissions).

Technical Data compliant with Kerakoll Quality Standard

Specific weight	1,6 g/cm ³
Coverage	da 1,5 a 3 kg/m ²
Application temperature	+5 °C / +35 °C
Application temperature range	-20 °C / +80 °C
Film formation time	≈ 60' (+23 °C, +50% R.H.)
Hardening speed	≈ 2,5 mm / 24 h (+23 °C, 50% R.H.)
Shelf life	≈ 18 months in the original packaging sealed and protected against damp
Pack	6 tins size 1 kg per box / 72 buckets per pallet

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e. temperature, ventilation and absorbcency level of the substrate and of the materials laid.

Performance**VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions**

Conformity	EC 1 plus GEV-Emicode	GEV certified 10952/11.01.02
------------	-----------------------	---------------------------------

HIGH-TECH

Shore A Hardness	50	ISO 868
Elongation at break	> 100%	ISO 37
Break strength	> 1,5 MPa	ISO 37
Shrinkage	≤ 5%	ISO 10563

Chemical resistance (information purposes only): to water, cleaning agents, accidental spillage of oils and hydrocarbons, acids, diluted alkalis.

colour chart

grey 7022	
Tile colour	

Other colours available on request. Shades shown are purely indicative.

Warning

- Product for professional use
- store in a well ventilated room at a maximum temperature of +30 °C

- see the safety data sheet
- for any other issues, contact the Kerakoll Worldwide Global Service +33 (0) 4 72 89 06 80 - globalservice@kerakoll.com

The Rating classifications refer to the GreenBuilding Rating Manual 2013. This information was last updated in June 2024 (ref. GBR Data Report - 06.24); please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.